

IN THE CLAIMS:

Claims 14 through 42 were previously cancelled. Claims 1 and 5 have been amended herein. All of the pending claims are presented below. This listing of claims will replace all prior versions and listings of claims in the application. Please enter these claims as amended.

Listing of Claims:

1. (Currently amended) An energetic thermoplastic elastomer, comprising:  
A blocks terminated with isocyanate-reactive groups derived from monomers ~~comprising at~~  
comprising at least one oxetane derivative, the A blocks being crystalline below about  
60°C;  
B blocks terminated with isocyanate-reactive groups derived from monomers comprising at least  
one member selected from the group consisting of oxirane and derivatives thereof, the B  
blocks being amorphous above about -20°C; and  
linking groups derived from at least one diisocyanate and at least one linking compound  
comprising two functional groups which are reactive with isocyanate moieties of the at  
least one diisocyanate.
2. (Previously presented) The energetic thermoplastic elastomer as defined in  
claim 1, wherein:  
the at least one diisocyanate contains a first isocyanate moiety which is at least five times more  
reactive with the terminal groups of the A blocks and the B blocks than a second  
isocyanate moiety thereof, wherein the first isocyanate moiety is capable of reacting with  
and end capping the terminal groups of the A blocks and the B blocks, leaving the second  
isocyanate moiety free and unreacted; and  
the at least one linking compound has two isocyanate-reactive groups which are sufficiently  
sterically unhindered to be reactive with the second isocyanate moiety of the end-capped  
A blocks and B blocks.

3. (Previously presented) The energetic thermoplastic elastomer as defined in claim 2, wherein the at least one diisocyanate comprises 2,4-toluene diisocyanate.
4. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein the A blocks are crystalline below about 75°C.
5. (Currently amended) The energetic thermoplastic elastomer as defined in claim 1, wherein the A blocks comprise homopolymers, copolymers, or terpolymers derived from at least one ~~symmetrically substituted~~ symmetrically substituted oxetane monomer comprising at least one member selected from the group consisting of 3,3-bis(methylnitraminomethyl)oxetane and 3,3-bis(azidomethyl)oxetane.
6. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein the B blocks comprise difunctional glycidyl azide polymer.
7. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein the B blocks comprise poly(glycidyl nitrate).
8. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein the energetic thermoplastic elastomer has a weight average molecular weight of at least 40,000 and a number average molecular weight of at least 10,000.
9. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein the energetic thermoplastic elastomer has a weight average molecular weight of at least 60,000 and a number average molecular weight of at least 12,000.

10. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein the energetic thermoplastic elastomer has a weight average molecular weight of at least 80,000 and a number average molecular weight of at least 15,000.

11. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein a weight ratio of A blocks to B blocks is between about 15:85 and about 40:60.

12. (Previously presented) The energetic thermoplastic elastomer as defined in claim 1, wherein the isocyanate-reactive terminal groups of the A blocks and the B blocks are hydroxyl groups.

13. (Previously presented) The energetic thermoplastic elastomer of claim 1, wherein the isocyanate-reactive terminal groups of the B blocks are secondary hydroxyl groups.

Claims 14-42 (Canceled)

43. (Previously presented) An energetic thermoplastic elastomer, comprising:  
A blocks terminated with isocyanate-reactive groups derived from monomers comprising at least one member selected from the group consisting of 3,3-bis(ethoxymethyl)oxetane, 3,3-bis(chloromethyl)oxetane, 3,3-bis(methoxymethyl)oxetane, 3,3-bis(fluoromethyl)oxetane, 3,3-bis(acetoxymethyl)oxetane, 3,3-bis(hydroxymethyl)oxetane, 3,3-bis(methoxyethoxymethyl)oxetane, 3,3-bis(iodomethyl)oxetane, 3,3-bis(nitratomethyl)oxetane, 3,3-bis(methylnitraminomethyl)oxetane, and 3,3-bis(azidomethyl)oxetane, the A blocks being crystalline below about 60°C;  
B blocks terminated with isocyanate-reactive groups and comprising at least one member selected from the group consisting of glycidyl azide polymer and poly(glycidyl nitrate), the B blocks being amorphous above about -20°C; and  
linking groups derived from at least one diisocyanate and at least one linking compound comprising two functional groups which are reactive with isocyanate moieties of the at least one diisocyanate.

44. (Previously presented) The energetic thermoplastic elastomer as defined in claim 43, wherein:  
the at least one diisocyanate contains a first isocyanate moiety which is at least five times more reactive with the terminal groups of the A blocks and the B blocks than a second isocyanate moiety thereof, wherein the first isocyanate moiety is capable of reacting with and end capping the terminal groups of the A blocks and the B blocks, leaving the second isocyanate moiety free and unreacted; and  
the at least one linking compound has two isocyanate-reactive groups which are sufficiently sterically unhindered to be reactive with the free and unreacted second isocyanate moiety of the end-capped A blocks and B blocks.

45. (Previously presented) The energetic thermoplastic elastomer as defined in claim 44, wherein the at least one diisocyanate comprises 2,4-toluene diisocyanate.

46. (Previously presented) The energetic thermoplastic elastomer as defined in claim 43, wherein the B blocks comprise difunctional glycidyl azide polymer.

47. (Previously presented) The energetic thermoplastic elastomer as defined in claim 43, wherein the B blocks comprise poly(glycidyl nitrate).

48. (Previously presented) The energetic thermoplastic elastomer of claim 1, wherein the A blocks terminated with isocyanate-reactive groups are derived from monomers comprising at least one member selected from the group consisting of 3,3-bis(ethoxymethyl)oxetane, 3,3-bis(chloromethyl)oxetane, 3,3-bis(methoxymethyl)oxetane, 3,3-bis(fluoromethyl)oxetane, 3,3-bis(acetoxymethyl)oxetane, 3,3-bis(hydroxymethyl)oxetane, 3,3-bis(methoxyethoxymethyl)oxetane, 3,3-bis(iodomethyl)oxetane, 3,3-bis(nitratomethyl)oxetane, 3,3-bis(methylnitraminomethyl)oxetane, and 3,3-bis(azidomethyl)oxetane.